

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
10 June 2004 (10.06.2004)

PCT

(10) International Publication Number  
**WO 2004/048652 A1**

- (51) International Patent Classification<sup>7</sup>: **D01F 6/60** 212, Gongdan-dong, Gumi-si, 730-030 Kyongsangbuk-do (KR).
- (21) International Application Number: PCT/KR2003/002523 (74) Agent: **CHO, Hwal-Rai**; Suite No. 1507 Yoksam Heights Bldg, 642-19, Yoksam-dong, Kangnam-Gu, 135-981 Seoul (KR).
- (22) International Filing Date: 21 November 2003 (21.11.2003)
- (25) Filing Language: Korean (81) Designated States (*national*): AE, AG, AL, AM, AU, AZ, BA, BB, BR, BY, BZ, CA, CN, CO, CR, CU, DM, DZ, EC, GD, GE, GH, GM, HR, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, RU, SC, SD, SG, SL, SY, TJ, TM, TN, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (26) Publication Language: English
- (30) Priority Data: 10-2002-0072977 22 November 2002 (22.11.2002) KR (84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (71) Applicant (*for all designated States except US*): **KOLON INDUSTRIES, INC** [KR/KR]; KOLON Tower, 1-23, Byulyang-dong, Kwacheon-city, 427-040 Kyunggi-do (KR).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **KIM, Jae-Young** [KR/KR]; 212, Gongdan-dong, Gumi-si, 730-030 Kyongsangbuk-do (KR). **PARK, Young-Tae** [KR/KR];

**Published:**

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: A FULL DULL POLYAMIDE 6 YARN, AND A PROCESS OF PREPARING FOR THE SAME

(57) Abstract: The present invention relates to a full dull polyamide 6 yarn and a process for preparing the same. The yarn of this invention contains 1.5 to 2.5 % by weight of titanium dioxide relative to the weight of the yarn, has 35 to 95 titanium dioxide particles having a major axial length of greater than 5µm being contained in 50 mg of the yarn, and contains 0.1 to 0.5 % by weight of phosphate salt (wetting agent) relative to the weight of titanium dioxide. In the process of this invention, 0.1 to 0.5 % by weight of phosphate salt relative to the weight of titanium dioxide is added as a wetting agent, caprolactam is applied along with water upon concentration correction, and naphthalene sulfonate based salt is applied along with titanium dioxide slurry during the process of polyamide 6 polymerization. The present invention improves the full dull effect and drape property of the yarn since it contains a great quantity of titanium dioxide having a proper diameter in the yarn without degrading the yarn physical properties and operationability.

WO 2004/048652 A1

**A FULL DULL POLYAMIDE 6 YARN, AND A PROCESS OF PREPARING  
FOR THE SAME**

TECHNICAL FIELD

5           The present invention relates to a full dull polyamide 6 yarn which  
is full dull and has an excellent weightiness (hereinafter refer to as "drape  
property") since it contains a great quantity of titanium dioxide within a  
yarn, and a process for preparing the same.

          Polyamide 6 yarns are being widely used for clothing as a  
10   substitute for natural yarns owing to excellent mechanical properties or  
the like. But, there is a problem that they show cold feeling and an  
excessively lightweight feeling due to a metallic brilliance and they are too  
transparent, thus they cannot satisfy the market demand valuing much  
of sensuous properties.

15

BACKGROUND ART

          To solve the above problem, there is being widely used the process  
of eliminating brilliance and improving drape property by applying an

inorganic material exhibiting a dulling effect during the process of polymerizing a polyamide 6 yarn. But, this process is problematic in that, when an input of the inorganic material is set high to 1.5% by weight relative to the weight of a yarn (polymer), the operationability is degraded  
5 and the yarn physical properties are deteriorated due to a nonuniform dispersion of the inorganic material.

Therefore, in the prior art, there is a limitation that an inorganic material of greater than 1.5% by weight cannot be contained in a polyamide 6 yarn, and accordingly, there is a limit to eliminate the  
10 metallic brilliance of the yarn or enhance the drape property.

The process of prior art, applying an inorganic material in a yarn, will be described in more detail. Slurry of inorganic material is prepared through a process of wetting an inorganic material with water, a process of grinding the inorganic material condensed in the above process, a  
15 concentration correction process, and a sedimentation process. Next, the slurry is applied during the polymerization process of polyamide 6, thereby to produce a full dull polyamide 6 yarn. As the inorganic material, mainly used is titanium dioxide having an average diameter of 0.3 to

0.4 $\mu$ m.

In the above process, the degradation of operationability and yarn physical properties does not occur only due to the original particle size of titanium dioxide, but it occurs because titanium dioxide is rapidly  
5 condensed during the wetting process.

In the above process of prior art, it is considered that the condensation of titanium dioxide in the wetting process is unavoidable. Thus, the problem of titanium dioxide condensation in the wetting process is overcome by such a process in which large particles of  
10 titanium dioxide are separated before titanium dioxide is applied in the polymerization process of polyamide 6, and only small particles are applied.

Due to this, the yield of the titanium dioxide slurry production process is degraded, the process becomes complicated because the  
15 separation process is added, and the particle size of titanium dioxide applied in the polymerization process is nonuniform.

Therefore, in the process of prior art, in a case that titanium dioxide of more than 1.5% by weight relative to the weight of a yarn

(polymer) is applied, there occurs a problem that the pressure of a pack (spinneret) is rapidly increased due to large diameter particles of titanium dioxide, and the yarn tension becomes nonuniform due to a nonuniform dispersion of titanium dioxide, to thereby make the bending and cutting  
5 of yarns disposed directly below the spinneret more serious.

In the prior art, the input of titanium dioxide cannot be set to more than a predetermined level due to the degradation of operationability and physical properties, and accordingly, it is restricted to improve the full dull property and drape property of polyamide 6 yarn.

10 Korean Laid-Open Patent No. 1999-60536 discloses a process for preparing a polyamide yarn by a high speed spinning, which produces a polyamide ultrafine yarn having a monofilament fineness of below 1.0 denier by adding titanium dioxide in the step of polyamide polymerization, wherein the portions directly below the spinneret are maintained at a  
15 heating atmosphere.

Although the detailed description of the above prior patent describes that titanium dioxide of 1 to 3% by weight is added in the polyamide polymerization step, every examples of the prior patent

describes that titanium dioxide of 1.5% by weight is added in the polyamide polymerization step.

This is because, as described above, in a case that titanium dioxide of more than 1.5% by weight is added in the polyamide polymerization  
5 step, there occurs a problem that the operationability is degraded and the yarn physical properties are deteriorated due to a nonuniform dispersion of titanium dioxide.

Moreover, the above prior patent does not suggests concrete means, for example, preparation conditions of slurry of titanium dioxide, for  
10 overcoming the above problems occurred upon applying titanium dioxide of more than 1.5% by weight in the polyamide polymerization step.

Subsequently, also in the Korean Laid-Open Patent No. 1999-60536, in a case that the amount of titanium dioxide is over 1.5% by weight, it is inevitable that there occur the degradation of the  
15 operationability and yarn physical properties due to a nonuniform dispersion of titanium dioxide.

As a prior art for improving the dispersability of titanium dioxide in polyamide, Korean Laid-Open Patent No. 2003-0012336 discloses a

process of applying 0.05 to 0.2 parts by weight of an amine based material relative to caprolactam monomer while using the existing viscosity stabilizer, i.e., an acetic acid.

However, the above prior art has a drawback that it is difficult to prevent recondensation fundamentally since a contact between acetic acid and titanium dioxide is possible, though the prior art may be effective to prevent the recondensation of titanium dioxide with an increase in repulsive force between titanium dioxide particle surfaces by pH control in the polymerization process. Further, since polymerization is typically carried out at a high temperature of higher than 250°C, in case of an amine based compound, there may occur a problem that its effect is not presented because the polymerization conditions such as a burning point, viscosity, etc. are not satisfied if a number of carbon atoms is below 10.

Additionally, since acid and amine are used in combination, the activity of polymerization may differ according to input equivalent ratio. This may be a factor in generating a difference in molecular weight of final polymer or a difference in terminal groups.

As another prior art, Korean Laid-Open Patent NO. 2003-0034845 discloses a process of applying 0.05 to 0.2 parts by weight of an aromatic amine relative to caprolactam without using acetic acid.

The above process allows to maintain a good dispersability of titanium dioxide in the polymerization process, but a reduction of zeta potential occurs at some portions in a reactor due to the abundance of the amine, to thereby deteriorate the dispersability of titanium dioxide on the contrary. In addition, the breadth of change in relative viscosity (RV) before and after melting increases due to an increase of terminal amine groups, and it is difficult to manage the strength of a final product. And, the above process is known to those skilled in the art as the process generally performed mainly for the purpose of improving deep color-dyeing or improving color difference. To complement the physical properties problem, the process of minimizing the breadth of change in relative viscosity (RV) before and after deep color-dyeing and melting by using an amine having no reactivity and being utilizable as a dyeing site is widely used.

Further, the above-described prior art processes all aim only to



maintain the dispersability of titanium dioxide in the polymerization process at a slurry level without mentioning detailed techniques for the production of titanium dioxide slurry. This shows that it is important to produce slurry of titanium dioxide with a good dispersability economically and efficiently.

In addition, in case of generally using a low molecular amine based compound, there is a possibility that polymerization may be accelerated by the reactivity of amine, and thus the color of a final polymer becomes poor.

Accordingly, it is an object of the present invention to provide a process for allowing much quantity of titanium dioxide to be contained in a yarn without degrading the operationability and physical properties by dispersing titanium dioxide uniformly in polymer by preventing the recondensation of titanium dioxide in a wetting process.

It is another object of the present invention to provide a polyamide 6 yarn which is full dull and has a good drape property since it contains a much quantity of titanium dioxide.

## DISCLOSURE OF THE INVENTION

The present invention provides a process for adding much quantity of titanium dioxide in a yarn (polymer) without degrading the operationability and the physical properties of yarns by minimizing the diameter of titanium dioxide to be applied in the step of polyamide 6  
5 polymerization and dispersing the applied titanium dioxide uniformly.

In addition, the present invention provides a polyamide 6 yarn which is full dull and has an excellent drape property since much quantity of titanium dioxide having a proper diameter is uniformly  
10 contained in the yarn.

To achieve the above objects, the present invention provides a full dull polyamide 6 yarn, which contains 1.5 to 2.5% by weight of titanium dioxide relative to the weight of the yarn, which has 35 to 95 titanium dioxide particles having a major axial length of greater than 5 $\mu$ m being  
15 contained in 50mg of the yarn, and which contains 0.1 to 0.5% by weight of phosphate salt (wetting agent) relative to the weight of titanium dioxide.

Additionally, the present invention provides a process for

preparing a full dull polyamide 6 yarn, in which the full dull polyamide 6 yarn is produced by preparing titanium dioxide slurry through wetting, grinding, concentration correcting, sedimentation and storage processes and applying the same during the process of polyamide 6 polymerization, wherein 0.1 to 0.5% by weight of phosphate salt relative to the weight of titanium dioxide is added as a wetting agent, caprolactam is applied along with water upon concentration correction, and naphthalene sulfonate based salt is applied along with titanium dioxide slurry during the process of polyamide 6 polymerization.

Hereinafter, the present invention will be described in detail.

Firstly, titanium dioxide slurry is prepared through wetting, grinding, concentration correction, sedimentation and storage processes. In the wetting process, a titanium dioxide powder is wet with water, a dispersion medium, in the ratio of 50:50. Then, 0.1 to 0.5% by weight of phosphate salt, such as sodium biphosphate, is added as a wetting agent relative to the weight of titanium dioxide, and stirred.

A typical polyamide 6 polymerization is carried out in such a step that a predetermined amount of water is put into caprolactam, a major

material, then ring-opening reaction is performed, and then polycondensation is performed, thereby making a final polymer. Thus, the reaction is conducted with a predetermined amount of water being contained within a reaction system. Hence, in the production process of titanium dioxide slurry, water is utilized as a dispersion media for wetting titanium dioxide of a powdery state to turn it into a liquid state under an economical condition.

The wetting agent is applied in order to reduce the cycle of the wetting process by increasing the affinity between water and titanium dioxide and minimize a particle size as much as possible right after the wetting process.

The wetting agent is such a material in which an ionic bond and a covalent bond coexist. It firstly increases the affinity between water and titanium dioxide through an electric charge, and, further, serves to control an electrical attractive force related to the condensation in a subsequent process of titanium dioxide slurry production.

In case of applying the wetting agent of below 0.1% by weight relative to the weight of titanium dioxide, the above-mentioned effect is

rarely exhibited. In case of applying the wetting agent of over 0.5% by weight, the extent of increase of affinity becomes smaller as compared to when the wetting agent of 0.5% by weight is applied, thus the production cost is increased. In case of applying an extremely large amount, this may  
5 occur adverse effects from a condensation viewpoint.

But, this does not mean that final titanium dioxide slurry is completed in the wetting process. The primary objective of the wetting process is to wet titanium dioxide of a powdery state with water, i.e., a dispersion medium most efficiently, and, in addition, to provide the  
10 foundation enabling a good dispersion in the subsequent titanium dioxide slurry production process.

In a case that the average particle diameter of titanium dioxide powder is 0.3 to 0.4 $\mu$ m, after the wetting process of the present invention, the average particle diameter of titanium dioxide becomes about 0.6 $\mu$ m.

15 To solve the problem of physical condensation of titanium dioxide occurring in the wetting process, it is preferred that stirring is performed for one hour at a low speed and for one hour at a high speed. The stirring speed is set to a proper level in conjunction with a geometric structure of

a stirring tank. In case of stirring at a high speed from an initial stage, wetting efficiency may be lowered due to an excessive heat generated in the stirring. Thus, it is preferred that the stirring is performed at a low speed at an initial stage, and, after a predetermined time, performed at a  
5 high speed.

After the wetting process, the titanium dioxide slurry made in the wetting process is made finer and uniformly dispersed through a grinding process. Preferably, the grinding process is performed repetitively about two times using a sand grinder filled with about 20% by weight of  
10 zirconium fill. However, the present invention does not specifically limit the grinding process.

Preferably, upon grinding, the flow rate of titanium dioxide slurry is maintained at 5 to 20kg/min, and the temperature of titanium dioxide grinded is maintained at 35 to 50°C.

15 After the grinding process, the concentration of titanium dioxide is corrected so that the grinded titanium dioxide slurry can have such a concentration capable of allowing the titanium dioxide slurry to have the most stabilized state.

Most preferably, the concentration is corrected with water, i.e., a dispersion medium. But, in case of correcting the concentration by increasing in weight of water, the dispersion stability of the titanium dioxide slurry is reduced because the apparent viscosity of the titanium dioxide slurry is lowered, whereby titanium dioxide particles may be recondensed.

In addition, the amount of water is increased in the subsequent polymerization process to arouse an excessive ring-opening reaction and, further, cause the problem of decrease in polymerization speed. For this reason, the present invention is characterized in that, upon concentration correction, caprolactam, which is a main material, is mixed with water at a predetermined ratio.

The amount of caprolactam to be applied is preferably 25 to 35% by weight relative to the total quantity of titanium dioxide slurry. The reason thereof is that, since final titanium dioxide slurry is made through sedimentation for four days after the step of concentration correction, the sorting efficiency of titanium dioxide through sedimentation is more increased if the amount of caprolactam is more decreased from a

sedimentation viewpoint.

And, as the amount of caprolactam is increased, dielectric constant of the slurry is lowered to thus increase condensation. From this viewpoint, the less the amount of caprolactam is, the better.

- 5 Immediately after the concentration correction, simple sedimentation is carried out in a concentration correction tank for one day to thus reduce final sedimentation load.

Next, sedimentation is performed to the titanium dioxide slurry compensation-corrected and simply sedimented as above. In the  
10 sedimentation process, final titanium dioxide slurry with a minimized average diameter is made through a long time sedimentation for four days.

The sedimentation velocity (or settling velocity) in a sedimentation tank is inverse proportional to the viscosity of a dispersion medium and  
15 the height of the sedimentation tank, and proportional to the temperature of a dispersion medium, the acceleration of gravity, the density of titanium dioxide and the like. Of them, the adjustable variables in the process are the height of the sedimentation tank, the temperature



of the dispersion medium and so on, and the proper conditions for these variables are selected as follows.

It is measured whether the average particle size of final titanium dioxide slurry sorted through sedimentation in the sedimentation tank  
5 for four days is consistent with a required level, and then the above variables are adjusted according to the result of the measurement.

In the present invention, according to the result of measurement by a particle size analyzer, the average particle size of titanium dioxide in the final titanium dioxide slurry is  $0.38\mu\text{m}$ . The particle concentration of  
10 titanium dioxide in the titanium dioxide slurry is 18.5 to 22.0% by weight upon measuring by a standard gravimeter at  $20^{\circ}\text{C}$ .

Next, the sorted titanium dioxide slurry is stored. In the above storage process, it is important to reduce a detention time as much as possible since the slurry is stored right before being applied into the  
15 process. And, to prevent settlement during detention, it is preferable to keep the temperature low.

The titanium dioxide slurry made as above has an excellent dispersability, so it is possible to apply a greater content thereof than that

applied in the prior art.

Next, the thusly made titanium dioxide slurry is supplied to a polyamide 6 polymerization system to thus produce a full dull polyamide 6 yarn. At this time, the present invention is characterized in that a  
5 naphthalene sulfonate based salt is applied together as a dispersion agent.

In other words, when the titanium dioxide slurry is applied in the polymerization, condensation may occur again. Thus, in the present invention, the recondensation of titanium dioxide particles in the  
10 polyamide polymerization process is controlled by adjusting electric potential with the applied naphthalene sulfonate based salt. The amount of the dispersion agent applied in this invention is preferably 30 to 60cc relative to 1kg of titanium dioxide particles.

The thusly produced polyamide 6 yarn (polymer) of this invention  
15 is very excellent in the dispersability of titanium dioxide particles, and is very excellent in full dull property and drape property since a great quantity of titanium dioxide, that is, 1.5 to 2.5% by weight, is contained relative to the weight of the yarn. In addition, the polyamide 6 yarn

(polymer) of the present invention has 35 to 95 particles of titanium dioxide having a major axial length of greater than 5 $\mu$ m in 50mg of the yarn (polymer).

Additionally, the polyamide 6 yarn (polymer) of this invention  
5 contains 0.1 to 0.5% by weight of phosphate salt (wetting agent) relative to the weight of titanium dioxide.

The operationability of preparing the yarn of this invention is good, which is the same level as the operationability of the prior art production process of a polyamide 6 yarn containing 0.3 to 0.4% by weight of  
10 titanium dioxide.

Various physical properties of the yarn (polymer) in the present invention are evaluated as follows.

• Number of Coarse Particles

15 It means the number of condensed titanium dioxide particles having a major axial length of greater than 5 $\mu$ m contained in 50mg of a polyamide 6 yarn (polymer). A sheet of slide glass is placed on a hot plate of 250°C, a sheet of glass film is placed thereon, 50mg of the yarn

(polymer) is placed and melted thereon, and then a sheet of cover glass is covered thereon. Next, the yarn is pressed by 200g of a weight to be thinly stretched, and then the entire regions of the sample are scanned by a light microscope of total 200 magnifications, thereby to measure the  
5 number of condensed titanium dioxide particles having a size of greater than 5 $\mu$ m.

Besides the above-mentioned hot plate process, among the sample preparation processs for measuring the number of condensed titanium dioxide particles, there is the process of using a small-sized extruder with  
10 a T-shaped spinneret. In this process, an undrawn film is prepared by a small-sized extruder, cooled by a casting drum, and then cut to a size proper to a drawing machine. The cut undrawn film is simultaneously biaxially oriented, and then heat-treated to prepare a sample for measurement. At this time, the temperature of the small-sized extruder is  
15 about 260 to 280°C, and the casting drum after the spinneret is maintained at 10°C, thereby to produce an undrawn film. The undrawn film is simultaneously biaxially oriented three times transversely and longitudinally each at about 55°C, and then thermoset for 30 seconds at

about 200°C, thereby to produce a final measurement sample.

• Content of Wetting Agent

A polyamide 6 yarn is pre-treated by the wet oxidation process and  
5 the oxidizer application and decomposition process, and then the content  
of a wetting agent is measured by an inductively coupled plasma mass  
analyzer (a product of VG ELEMENTAL, model name: Plasma Quad3).

• Dispersability of Titanium Dioxide

10 A specimen made by slicing a polyamide 6 yarn (polymer) by a  
cutter of Microtom is immersed on a sheet of slide glass with paraffin, a  
sheet of cover glass is covered thereon, and projection photographs of 10  
areas are taken by a light microscope of 625 magnifications. Condensed  
titanium dioxide particles are found from each of the photographs, and  
15 the size and number thereof are arranged. Among 10 results arranged,  
the dispersability of titanium dioxide is judged according to the  
remaining 8 results, except for the best result and the worst result. Of the  
8 results, if more than 7 results are excellent, it is represented as ◎, if 5

to 6 results are excellent, it is represented as ○, and if less than 4 results are excellent, it is represented as △.

• Operationability (Full Drum Rate – F/D rate)

5        The operationability is indicated by the F/D rate showing the ratio of the number of full drums that are fully wound per the total number of drums manufactured in a spinning process.

$$\text{Operationability (F/D rate)} = \frac{\text{number of full drums}}{\text{total number of drums}} \times 100(\%)$$

10        • Full Dull Property

Yarns are tube-knitted and then evaluated by an organoleptic test by panelists. Of five panelists with over seven year's career, if more than four people agree that the full dull property is excellent, it is indicated as ◎, if two or three people agree that the full dull property is excellent, it is indicated as ○, and less than one people agrees that the full dull property is excellent, it is indicated as △.

15

• Drape Property

A cloth made by tube-knitting yarns is cut to a circular shape having a 25cm diameter, then placed over a cylinder having a 12.5cm diameter, and then evaluated in drape property according to how long the cloth is draped down (drape coefficient: F). If the drape coefficient (F) is less than 0.3, it is indicated as ◎, and if the drape coefficient (F) is more than 0.3, it is indicated as △. The drape coefficient is calculated by the following formula:

$$\text{Drape Coefficient}(F) = \frac{r^2 - rd^2}{rD^2 - rd^2}$$

Wherein rD represents the radius of a completely hard twist fabric, rd represents the radius of a completely soft twist fabric, and r represents the radius of a specimen.

### BEST MODE FOR CARRYING OUT THE INVENTION

The present invention is now understood more concretely by comparison between examples of the present invention and comparative examples. However, the present invention is not limited to such  
5 examples.

#### Example 1

Titanium dioxide with an average diameter of 0.3 $\mu$ m is wet with water in the ratio of 50:50, then added with 0.3% by weight of sodium  
10 biphosphate (wetting agent) relative to the weight of titanium dioxide and stirred, and then grinded with a sand grinder.

Next, the concentration of titanium dioxide slurry is corrected by using water and 30% by weight of caprolactam relative to the weight of titanium dioxide slurry, and then the titanium dioxide slurry is immersed  
15 for four days, thereby to prepare final titanium dioxide slurry.

Next, the titanium dioxide slurry is applied in a polyamide 6 polymerization process along with sodium naphthalene sulfonate (dispersion agent) in a 20% aqueous solution state to thus produce a polyamide 6 polymer. The polyamide 6 polymer is composed of 100% by



weight of caprolactam, 5.3 parts by weight of water and 0.1 parts by weight of acetic acid.

Here, the titanium dioxide slurry is applied in such a composition in which the quantity of titanium dioxide particles can be 1.8 parts by weight relative to 100 parts by weight of caprolactam. The dispersion agent is applied so that it can be 40cc per 1kg of titanium dioxide particles. The thusly produced polyamide 6 polymer is spun in a typical spin-direct-draw condition, to thus produce a polyamide 6 yarn having 70 deniers and 36 filaments. The result of evaluating the physical properties of the produced yarn and operationability is as shown in Table 2.

#### Examples 2 to 7 and Comparative Examples 1 and 2

Except that the quantity of titanium dioxide particles, the input of a dispersion agent and the input of a wetting agent are changed as in Table 1, a polyamide 6 polymer and yarn are produced in the same process and condition as Example 1. The result of evaluating the physical properties of the produced yarn and operationability is as shown in Table 2.

[Table 1]

## Production Condition

Classification	Input of titanium dioxide relative to 100 parts by weight of caprolactam (parts by weight)	Input of dispersion agent per 1kg of titanium dioxide particles (cc)	Input of wetting agent relative to weight of titanium dioxide (% by weight)
Example 1	1.8	40	0.3
Example 2	1.6	40	0.3
Example 3	2.4	40	0.3
Example 4	1.8	35	0.3
Example 5	1.8	60	0.3
Example 6	1.8	40	0.1
Example 7	1.8	40	0.5
Comparative Example 1	1.3	0	0
Comparative Example 2	2.6	0	0

[Table 2]

## Result of Evaluation of Physical Properties

Classification	Operability (F/D rate) [%]	Number of condensed particles (개)	Content of titanium dioxide (% by weight)	Dispersability of titanium dioxide	Full dull property	Drape property
Example 1	98.1	64	1.8	◎	◎	◎
Example 2	98.3	47	1.6	◎	◎	◎
Example 3	96.2	94	2.4	◎	◎	◎
Example 4	97.0	77	1.8	◎	◎	◎
Example 5	98.3	57	1.8	◎	◎	◎
Example 6	97.3	83	1.8	◎	◎	◎
Example 7	97.6	64	1.8	◎	◎	◎
Comparative Example 1	98.5	33	1.3	◎	△	△
Comparative Example 2	92.1	137	2.6	△	○	△

\* The content of titanium dioxide is % by weight relative to the weight of yarn.

### INDUSTRIAL APPLICABILITY

The present invention can prevent the degradation of operationability and yarn physical properties since a great quantity of titanium dioxide having a proper diameter are uniformly dispersed in a  
5 polyamide 6 yarn. In addition, the polyamide 6 yarn of this invention uniformly contains titanium dioxide with a proper diameter, thus it has no metallic brilliance and has an excellent drape property.

## WHAT IS CLAIMED IS:

1. A full dull polyamide 6 yarn, which contains 1.5 to 2.5% by weight of titanium dioxide relative to the weight of the yarn, which has 35 to 95 titanium dioxide particles having a major axial length of greater than 5 $\mu$ m being contained in 50mg of the yarn, and which contains 0.1 to 0.5% by weight of phosphate salt (wetting agent) relative to the weight of titanium dioxide.

2. A process for preparing a full dull polyamide 6 yarn, in which the full dull polyamide 6 yarn is produced by preparing titanium dioxide slurry through wetting, grinding, concentration correcting, sedimentation and storage processes and applying the same during the process of polyamide 6 polymerization, wherein 0.1 to 0.5% by weight of phosphate salt relative to the weight of titanium dioxide is added as a wetting agent, caprolactam is applied along with water upon concentration correction, and naphthalene sulfonate based salt is applied along with titanium dioxide slurry during the process of polyamide 6 polymerization.



3. The process of claim 2, wherein the input of caprolactam is 25 to

35% by weight relative to the weight of the titanium dioxide slurry.

4. The process of claim 2, wherein the input of naphthalene sulfonate based salt is 30 to 60cc per 1kg of titanium dioxide particles.

## INTERNATIONAL SEARCH REPORT

National application No.  
PCT/KR2003/002523

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> <b>IPC7 D01F 6/60</b> According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC7 D01F, D01D, C08G  Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched KR, JP :IPC as above  Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 54-151620 A (TEIJIN LTD.) 29 NOVEMBER 1979 (29.11.1979) (Family None) see the whole document	1 - 4
A	JP 60-112849 A (TEIJIN LTD.) 19 JUNE 1985 (19.06.1985) (Family None) see the whole document	1 - 4
A	KR 1996-84 A (SAMYANG CO.) 03 JANUARY 1996 (03.01.1996) (Family None) see the whole document	1 - 4
A	KR 1996-22661 A (KOHAP LTD.) 18 JULY 1996 (18.07.1996) (Family None) see the whole document	1 - 4
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
<p>* Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&amp;" document member of the same patent family</p>		
Date of the actual completion of the international search 25 FEBRUARY 2004 (25.02.2004)		Date of mailing of the international search report 25 FEBRUARY 2004 (25.02.2004)
Name and mailing address of the ISA/KR  Korean Intellectual Property Office 920 Dunsan-dong, Seo-gu, Daejeon 302-701, Republic of Korea Facsimile No. 82-42-472-7140		Authorized officer OH, SANG KYUN  Telephone No. 82-42-481-8165